PCCP

Accepted Manuscript

This article can be cited before page numbers have been issued, to do this please use: G. J. Soldano, F. M. Zanotto and M. M. Mariscal, *Phys. Chem. Chem. Phys.*, 2016, DOI: 10.1039/C5CP07797D.

This is an *Accepted Manuscript*, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this *Accepted Manuscript* with the edited and formatted *Advance Article* as soon as it is available.

You can find more information about *Accepted Manuscripts* in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this *Accepted Manuscript* or any consequences arising from the use of any information it contains.

Mechanochemical stability of sub-nm ZnO chains[†]

Germán J. Soldano,* Franco M. Zanotto, and Marcelo M. Mariscal

Received Xth XXXXXXXXXX 20XX, Accepted Xth XXXXXXXXXX 20XX

First published on the web Xth XXXXXXXXXX 200X

DOI: 10.1039/b000000x

Formation of monoatomic chains by axial stretching of zinc oxide nanowires is investigated by molecular dynamics and supported by density functional calculations. Special focus is made on the mechanical properties of these structures. Using a state-of-the-art force field it was found that O₂ species are commonly formed within the chain. This species drastically weakens the chain strength. Previous simulations, based on a pair potential, failed to predict O₂ formation. Moreover, the superductility of zinc oxide nanowires observed in earlier works, was found to be an artifact of the pair potential. Simulations revealed that the chain length before rupture (usually of 6 atoms) is independent of the nanowire diameter. The electronic structure and charge distribution of the chains were also studied.

1 Introduction

Few materials are more versatile than zinc oxide, as it is reflected in its large number of application fields. It is used as protective coating,¹ photocatalyst,¹ antibacterial agent,² and ceramic additive.³ Its applications are not restricted to the macroscopic scale.⁴ ZnO nanowires are employed in gas and chemical sensing, transparent conductors, electro-optic devices, and solar cells.^{5–7} Still, the most interesting features of ZnO are yet to be exploited. Having a wide band gap of 3.37 eV at room temperature, ZnO could be used for short-wavelength devices.^{8,9} Due to its large exciton binding energy (60 meV) low cost, and biocompatibility, ZnO appears as the best candidate for the practical use of quantum dots.¹⁰ Another promising application is in nanogenerators,¹¹ which make use of the piezoelectric property of ZnO to convert microbiological motion into electricity. These and several other applications are maximized when the oxide is built as one-dimensional (1-D) structures. ZnO nanowires, for instance, can stand five times more strain than the bulk material, and therefore induce five times more voltage.¹²

1-D ZnO nanostructures can be synthesized by thermal evaporation¹³ or chemical vapor deposition.¹⁴ According to electron microscopy observations, the most common structure of ZnO nanowires is the wurtzite structure,^{14,15} which is also the most stable bulk phase. These studies also revealed that as-grown ZnO nanowires have well-defined shape with high aspect ratio. As first attempts to study their mechanical properties, several studies have been advocated to measure

the Young's modulus using bending resonance,^{16–21} bending deflection,^{22–24} nanoindentation,^{20,25} and tensile stretching.^{26–28} According to AFM measurements, the efficiency for converting mechanical to electrical energy on ZnO NWs can reach up to 30%.¹¹ Characterization and manipulation of these nanostructures implies a great experimental challenge. For this reason, computational approaches such as molecular dynamics (MD) and density functional theory (DFT) have become useful allies. DFT calculations showed that for diameters lower than 9 Å, nanotubes are actually more stable than nanowires.²⁹ Several DFT studies have focus on the mechanical response of ZnO NWs upon tensile loading^{30–32} although with important limitations such as i) they were based on static calculations; ii) the temperature effect was neglected; and iii) the NWs studied were rather small. Few MD simulations were performed without such restrictions and unexpected results were obtained. It was found that under tensile stress ZnO NWs change from wurtzite to a body-centered-tetragonal (BCT) structure.^{33–37} Another intriguing result is their *super ductility*. After brittle failure and necking, single-atom chains were formed. In these simulations chains achieved lengths of dozens of atoms.^{38,39} A central aspect that should not be overlooked in these studies is the potential used. The Buckingham (BCK) potential^{40,41} is a non-reactive pair potential, so that bond breaking and bond formation are not contemplated. These processes are nonetheless essential to describe phase transition, brittle failure, and necking, which are the central features in which the latter studies are based on. It is also important to notice that the BCK potential was not parametrized for nanostructures, but for the bulk crystal. Another weakness of the potential is that the atomic charges are fixed.

In a recent publication we studied the phase transition of ZnO nanowires upon tensile loading⁴² and found a substantial improvement in the description of the Zn-O bond with a re-

INFIQC - Departamento de Matemática y Física - Facultad de Ciencias Químicas Universidad Nacional de Córdoba, Argentina. Fax: +49 731 50 22819, Tel: +49 731 50 31340, *e-mail: german.soldano@unc.edu.ar

[†] Electronic Supplementary Information (ESI) available: videos and figures are available. See DOI: 10.1039/b000000x/

Fig. 1 Stages of axial stretching of NW_{II} at 300 K. Oxygen and zinc atoms are colored red and grey, respectively. (a) equilibrium state, (b) elastic stretching, (c) brittle failure, neck formation, and plastic stretching, (d) neck thinning, (e) nanoladder formation, (f) monoatomic chain formation with a O₂ species within the chain, (g) final break.

active force field^{43,44} (ReaxFF). Using the same approach we now focus on the mechanochemical stability of ZnO atomic chains formed after nanowire necking. In contrast with previous works,^{38,39} it was found that these chains do not grow indefinitely, but normally reach to a length of six atoms before breaking. Moreover, an unprecedented chain structure containing an oxygen-oxygen bond was found to be the most common one. Several outcomes of these simulations were tested with DFT calculations and found to be in excellent agreement. Chain stress during tensile loading was also investigated. For the sake of completeness, charges density difference, density of states, and band gaps of these sub-nm structures were also studied.

2 Computational Details

Energy minimizations and molecular dynamics simulations (MD) were carried out using the Large-scale Atomic-Molecular Massively Parallel Simulator (LAMMPS)⁴⁵ with its ReaxFF subroutine,⁴⁶ which describes the O-Zn interaction.^{43,44} The simulations were performed with a constant number of atoms and constant temperature using the Nose-Hoover thermostat, with a time-step of 0.5 fs.

All nanowires in this work are [0001] oriented wurtzite structures with hexagonal cross-section exposing the {10 $\bar{1}$ 0} facets. For MD simulations, seven ZnO bilayers were used to account for the possible surface reconstructions. Periodic boundary conditions were implemented in three dimensions, keeping the nanowires separated by at least 20 Å with respect to their periodic images. The length of the simulation box

along the wire axis was increased at 0.8 m/s and 8.0 m/s, simulating tensile loading at two speeds. Slower stretchings did not affect the results. Initial velocities were randomly assigned following a Maxwell-Boltzmann distribution. Tensile stress was obtained as the sum of the *z* component of the stress tensor of each atom, as calculated by the compute_stress_atom subroutine included in LAMMPS. Studies of chain stretching were performed by tips that pulled the chains at a constant speed of 0.01 m/s.

Ab initio calculations were performed using the Quantum Espresso/PWSCF code.⁴⁷ Vanderbilt ultrasoft pseudopotentials⁴⁸ were used with the Perdew-Burke-Ernzerhof (PBE)⁴⁹ approximation. A 36 Ry kinetic energy cutoff and a 300 Ry charge density cutoff was used. Reciprocal space of the monoatomic chains was sampled with a (10×1×1) k-point grid using the Monkhorst-Pack method⁵⁰ for the primitive unit cell, which consists of a single pair of zinc and oxygen atoms. For larger cells the k-point grid was reduced proportionally. All these inputs were carefully parameterized. A Gaussian broadening of 0.01 Ry was applied. Relaxations were converged when the forces were less than 0.02 eV/Å. Unit cells were big enough so that the atomic chains were separated at least 12 Å from their periodic images.

3 Results and Discussion

Five MD runs were carried out on each of the nanowires of different diameters (detailed in Table 1) at 300 K. Under these conditions the nanowires do not suffer a phase transition, as we have discussed in a previous work.⁴² The unit cell was

	NW ₀	NW _I	NW _{II}	NW _{III}	NW _{IV}	NW _V
$d[\text{\AA}]$	3.6	9.6	16.8	23.2	29.4	36.2
n	84	336	756	1344	2100	3024

Table 1 Diameter (d) and number of atoms per unit cell (n) of the ZnO nanowires simulated in this work.

elongated at 0.8 m/s along the nanowire axis in order to simulate tensile loading. At the initial state, nanowires are axially compressed with respect to their equilibrium length. When stretched they show a series of structural changes which stages are summarized in Fig. 1. First, the distance of the atoms along the nanowire axis increases (Fig. 1a-b). A plot of the tensile stress as a function of strain (Fig. 2), reveals that this stage corresponds to an elastic deformation. This implies that

Fig. 2 Tensile stress as a function of strain for NW_{II} as a typical example. Labels from *a* to *g* correspond to stages shown in Fig. 1

a complete recoverability from strain is achieved if the stress is removed. In the following stage the nanowire suffers irreversible restructuring within a localized region, leading to the formation of an amorphous neck (Fig. 1c). Within the neck the load is relieved by local relaxation, while far from the neck the atoms return to their equilibrium crystalline positions. Consequently, the tensile stress jumps abruptly to lower values (first stress break in Fig. 2). As the stretching continues, further atomic reconfigurations, bond breaking, and relaxations take place in the neck region. Among other processes, the formation of oxygen-oxygen bonds has been observed there. This stage corresponds to a mechanism of plastic deformations, characterized by subsequent increments and steep drops of the tensile stress. As the stretching continues, the wire neck gets thinner and thinner, until a single-atom chain of zinc-oxygen bonds is formed (Fig. 1d-f). By pulling atoms from the neck the chain may grow longer. Eventually, the chain breaks

(Fig. 1g) and the tensile stress drops to zero (Fig. 2). In most of the cases the chain rupture occurs after the formation of an oxygen-oxygen bond within the chain (Fig. 1f) as a consequence of an O₂-Zn bond breakage. In larger nanowires more than one chain can be formed after necking. Although the formation of monoatomic chains has been reported before,^{38,39} to the best of our knowledge, this is the first time that an oxygen-oxygen bond has been observed within the chain. A movie showing the formation and rupture of such chains is given in the SI (see ZnO-NC-movie.gif).

In order to validate these results, DFT relaxations at several fixed unit cell lengths were carried out. Some relevant atomic distances obtained from these calculations are shown in Fig 3. The distance between zinc atoms may be of experimental interest as oxygen atoms are invisible to several microscopic techniques such as High Resolution Transmission Electron Microscopy (HRTEM). Distances between zinc neighbor atoms greater than 4 Å would indicate the presence of an O₂ species within the ZnO monoatomic chain. To examine the distance between zinc and oxygen atoms, two cases have to be distinguished. The distance between zinc atoms and atomic oxygen ($d_{\text{Zn-O}}$), and the distance between zinc atoms and O₂ species ($d_{\text{Zn-O}_2}$). As shown in Fig 3, $d_{\text{Zn-O}_2} > d_{\text{Zn-O}}$ at every stage of strain. Moreover, the difference between these two increases with the strain. This implies that the Zn-O₂ bond weakens with the stretching faster than the Zn-O bond. Interestingly, the distance between oxygen atoms in O₂ species decreases with the strain, showing that the O-O bond actually gets stronger during the chain stretching. These facts are clear signs that ZnO chains break at the O₂-Zn bond, which is precisely what our MD simulations show.

Besides monoatomic chains, another structure is commonly observed in simulations after necking: ZnO ladders (Fig. 1e). They consist of two atomic chains connected sideways so that each oxygen atom is bonded to three zinc atoms and vice versa. In order to compare performances of ReaxFF and BCK with DFT on nanostructures, stretching studies on chains and ladders were carried out using these three techniques. A detailed analysis is given in the SI-Fig.2-4. We found that the BCK potential fails to describe the oxygen-oxygen interaction. Regardless of the starting configuration of a chain containing O₂, the BCK potential tends to rearrange the structure in order to avoid the oxygen-oxygen bond. This is simply because in this potential the charges are fixed and the O₂ species implies a repulsive anion-anion interaction. Relaxations of such chains using the force field, on the other hand, are in good agreement with that of DFT (SI Fig.3). The same applies for chains without O₂ and ladders, where energy and geometry obtained from ReaxFF are closer to DFT predictions (SI-Fig.2 and SI-Fig.4). These results show that the reactive force field gives better qualitative and quantitative descriptions of ZnO nanostructures than the Buckingham potential.

Fig. 3 Relevant atomic distances in a ZnO chain containing O_2 during relaxed stretching performed with DFT. Appearance of two O_2 species in the chain is due to periodic boundary conditions.

In order to estimate the average length of the atomic chains right before nanowire rupture, statistical analysis was performed over sets of 50 MD runs for each nanowire. The strain speed has little effect on the distribution of chain lengths (SI-Fig.5), therefore, calculations were performed at the fast stretching speed (8.0 m/s). Fig. 4 shows histograms of chain lengths for four nanowires of increasing diameter. Notably, the atomic chain length before rupture is independent of the nanowire diameter. More than 80% of these chains present O_2 species. When such a species is present in the chain, the rupture occurs at the O_2 -Zn bond. Histograms of Fig. 4 reveal that the most common chain length before rupture is of six atoms. These results demonstrate that the super ductility of ZnO nanowires is actually an artifact of the BCK potential.

Due to the uncontrolled restructuring of the neck, it is difficult to study the average tensile stress of chains from simulations described above. In order to do so, the stretch was

Fig. 4 Histograms of chain length before rupture for four nanowires of different diameter at a stretching speed of 8.0 m/s . 50 MD runs at 300 K were performed per nanowire.

simulated in a controlled system consisting of two tips pulling the chain along its axis, as shown in Fig. 5a. The figure also shows two types of chains, one with and one without the O_2 species (NC2 and NC1, respectively). Chains are terminated with an oxygen atom which is bonded to three zinc atoms of the tip. With the exception of these three, the relative positions of the atoms in the tips are fixed during the strain. Therefore, the chains can not grow during the simulations. For each chain type 50 MD runs were carried out. The corresponding stress-strain curves are shown in Fig. 5b. It was found that NC1 supports larger strains and almost 50% more stress than NC2. This entails that NC2 has less strength to pull atoms from the neck, which in turn is in line with the observation that chains are often broken right after the incorporation of O_2 . Also, the elastic modulus of NC2 is found to be lower than that of NC1. This softening effect due to the inclusion of O_2 species is notably different from the two most common sources of such a phenomenon: structural defects and surface layers.^{51,52} Fig. 5c shows the effect of the strain on the bond angles of the chain. For NC1 and NC2, O-Zn-O and Zn-O-Zn angles are independent of the presence of O_2 up to the strain of fracture of NC2. In this strain window and in both wires, O-Zn-O sets keep their atoms almost aligned, so that it is the Zn-O-Zn the one which actually respond to the stretching. In NC2 the Zn-O-O angle experiences the largest change, which is in the order of 40 degrees. First neighbor distances of NC1 and NC2 as a function of strain are given in Fig. 5d. In excellent agreement with DFT predictions (Fig. 3) the Zn-O2 bond distance increases faster than that of the Zn-O bond and the O-O distance decreases with the strain. These results prove the transferability of the ReaxFF, since it gives correct trends

Fig. 5 (a) Top and side view of the tip that pulls the chains. (b-d) Comparison between 50 MD runs simulations performed on NC1 and NC2 chains. (b) Tensile stress as a function of the strain. (c) Angles between three adjacent atoms (the central one being the vertex) as function of the strain. (d) Relevant atomic distances as a function of the strain. Note the resemblance with DFT results in Fig. 3.

in structures that were not considered in its parametrization. Another important observation in Fig. 5d is that for NC2 the breakage occurs always in the Zn-O2 bond, which increases drastically at strains larger than 14%. The Zn-O distance, on the other hand, return to its equilibrium value after this point.

It is well known that ZnO bond has a strong ionic character and that the bond in the oxygen molecule is covalent. However, it is non trivial to predict the bond nature between atoms in a ZnO chain containing O₂. With this attempt, charge density differences were calculated according to eq. 1 using DFT.

$$\Delta\rho = \rho[\text{Zn}_m\text{O}_n] - m\rho[\text{Zn}_{at}] - n\rho[\text{O}_{at}] \quad (1)$$

$\rho[\text{Zn}_m\text{O}_n]$ is the electron density of the atomic chain; m and n the number of Zn and O atoms, respectively; and $\rho[\text{Zn}_{at}]$ and

$\rho[\text{O}_{at}]$ the electron density of Zn and O isolated atoms. Results for NC1 and NC2 are given in Fig 6. A typical ionic charge distribution is observed in the first case, with electron accumulation around oxygen atoms and electron depletion around Zn atoms. A similar distribution is observed in NC2, although in this case charge accumulation of atoms in the O₂ species is about half that of the other oxygen atoms. Also, blue regions appear at opposite sides of the O₂ bond and a subtle red region appears in between the oxygen atoms. Therefore, oxygen atoms in O₂ within the chain present both a ionic bond with zinc atoms and a covalent bond with each other. Another important aspect to study is the change of the atomic charge during the stretching. Voronoi charges⁵³ show that until breakage, such a change is negligible. After rupture,

Fig. 6 Charge density difference of NC1 and NC2 chains. Blue wireframes correspond to electron depletion and red wireframes to electron accumulation for a charge isovalue of $0.004 e/\text{\AA}^3$.

terminal atoms decrease their module charge by about 50%. Details are given in the SI.

As semiconductors, it is crucial to know the band gap of ZnO nanostructures. To the best of our knowledge, this has not been studied for ZnO atomic chains. Although current DFT functionals underestimate the energy gap in semiconductors and insulators, they give the correct tendency. For this reason, the band gaps of bulk, nanowires, and chains were compared. Density of states (DOS) of these structures are given in Fig 7a where a closer view around the Fermi energy is also shown. Our calculations for nanowires and bulk are in agreement with previous GGA studies, as shown in table 2. Band gap values

	NC1	NC2	NW ₀	NW _I	NW _{II}	bulk
this work	2.8	1.9	1.8	1.3	1.0	0.6
other works	–	–	2.0 ⁵⁴	1.5 ⁵⁴	1.1 ⁵⁴	0.7 ⁵⁵

Table 2 Band gaps of ZnO nanochains, nanowires, and bulk crystal.

as a function of nanostructures diameter is presented in Fig 7b. It is clear from these plots that the band gap increases with the thinning of the ZnO structures; the largest gap corresponds to NC1. The difference between the band gaps of NC1 and NC2 are due to the high energy of the O₂ π state, which decreases the energy difference with the corresponding excited states by ~ 0.8 eV (details given in the SI).

4 Conclusions

The most useful features of ZnO are revealed at the nanoscale. A deeper understanding of its mechanical properties in such a scale is essential. With this aim, the formation of sub-nm structures resulting from the tensile stress of ZnO nanowires

Fig. 7 (a) Total density of states of ZnO bulk, NW₀, NW_I, NW_{II}, NC1 and NC2. Bulk and NWs are in the wurtzite structure. Energies are given respect to the Fermi energy (E_f). Zoom near the Fermi level is also shown (right panels). (b) Band gap of the above structures as a function of their diameter. The value corresponding to the bulk crystal is also shown.

was investigated by molecular dynamics and density functional theory. In every case the axial stretching of nanowires led to the formation of atomic chains. More than 200 simulations of several nanowires revealed that such chains usually get to six atoms-long before breaking. They also showed that O₂ is formed within the chain in more than 80% of the cases. The latter chains always break due the rupture of the O₂-Zn bond. Geometrical and energetic aspects of this rupture are in perfect agreement with our DFT calculations. Simulations of chains pulled by tips showed that those without O₂ can stand stresses of about 65 GPa, while those with O₂ breaks at stresses of 45 GPa. DFT charge density difference revealed that the O₂ within the chain possesses both, covalent and ionic features. The band gap of chains with O₂ is close to that of the

thinnest nanowire (NW₀), while for those without it is about 0.8 eV higher.

Our DFT calculations proved that a reactive force field is more suited than previously used pair potentials to describe ZnO nanostructures. In fact, the use of pair potentials leads to misleading results such as superductility or ZnO chains without O₂ species. This work exemplifies how important it is to check simulation outcomes with DFT calculations in order to validate the use of potentials. Special care has to be taken when such potentials are to be tested in systems they were not parametrized for.

Most of ZnO applications required or involved an aqueous medium. A key aspect reserved for future studies is therefore the influence of water in the mechanical properties of these structures. We hope this work gives fundamental information to unravel more applications of ZnO at the nanoscale.

Acknowledgments

This investigation was supported by CONICET PIP 11220110100992 and 1122015 0100141, Universidad Nacional de Córdoba (UNC). The authors thank the Texas Advanced Computer Center (TACC) for access to the Stampede supercomputer and the Centro de Computación de Alto Desempeño (CCAD, UNC, Córdoba, Argentina) for access to the Cristina supercomputer. F.M.Z. thanks CIN for the fellowship granted.

References

- H. Benhebal, M. Chaib, T. Salmon, J. Geens, A. Leonard, S. D. Lambert, M. Crine and B. Heinrichs, *Alexandria Engineering Journal*, 2013, **52**, 517–523.
- N. Padmavathy and R. Vijayaraghavan, *Science and Technology of Advanced Materials*, 2008, **9**, 035004.
- A. Moezzi, A. M. McDonagh and M. B. Cortie, *Chemical Engineering Journal*, 2012, **185–186**, 1–22.
- Y. Zhang, M. K. Ram, E. K. Stefanakos and D. Y. Goswami, *J. Nanomaterials*, 2012, **2012**, 20:1–20:22.
- M. S. Arnold, P. Avouris, Z. W. Pan and Z. L. Wang, *The Journal of Physical Chemistry B*, 2003, **107**, 659–663.
- E. Comini, G. Faglia, G. Sberveglieri, Z. Pan and Z. L. Wang, *Applied Physics Letters*, 2002, **81**, 1869–1871.
- P. X. Gao, C. S. Lao, W. L. Hughes and Z. L. Wang, *Chemical Physics Letters*, 2005, **408**, 174–178.
- Z. K. Tang, G. K. L. Wong, P. Yu, M. Kawasaki, A. Ohtomo, H. Koinuma and Y. Segawa, *Applied Physics Letters*, 1998, **72**, 3270–3272.
- J. G. Lu, Z. Z. Ye, Y. Z. Zhang, Q. L. Liang, S. Fujita and Z. L. Wang, *Applied Physics Letters*, 2006, **89**, year.
- D. Wang, Y. C. Liu, R. Mu, J. Y. Zhang, Y. M. Lu, D. Z. Shen and X. W. Fan, *Journal of Physics: Condensed Matter*, 2004, **16**, 4635.
- Z. L. Wang and J. Song, *Science*, 2006, **312**, 242–246.
- R. Agrawal, B. Peng and H. D. Espinosa, *Nano Letters*, 2009, **9**, 4177–4183.
- J.-S. Lee, K. Park, M.-I. Kang, I.-W. Park, S.-W. Kim, W. K. Cho, H. S. Han and S. Kim, *Journal of Crystal Growth*, 2003, **254**, 423–431.
- P.-C. Chang, Z. Fan, D. Wang, W.-Y. Tseng, W.-A. Chiou, J. Hong, and J. G. Lu, *Chemistry of Materials*, 2004, **16**, 5133–5137.
- J. G. Lu, P. Chang and Z. Fan, *Materials Science and Engineering: R: Reports*, 2006, **52**, 49–91.
- X. D. Bai, P. X. Gao, Z. L. Wang and E. G. Wang, *Applied Physics Letters*, 2003, **82**, 4806–4808.
- K. Yum, Z. Wang, A. P. Suryavanshi and M.-F. Yu, *Journal of Applied Physics*, 2004, **96**, 3933–3938.
- C. Q. Chen, Y. Shi, Y. S. Zhang, J. Zhu and Y. J. Yan, *Physical Review Letters*, 2006, **96**, 075505–075508.
- Y. Huang, X. Bai and Y. Zhang, *Journal of Physics: Condensed Matter*, 2006, **18**, L179.
- H. Ni and X. Li, *Nanotechnology*, 2006, **17**, 3591.
- J. Zhou, C. S. Lao, P. Gao, W. Mai, W. L. Hughes, S. Z. Deng, N. S. Xu and Z. L. Wang, *Solid State Communications*, 2006, **139**, 222–226.
- J. Song, X. Wang, E. Riedo and Z. L. Wang, *Nano Letters*, 2005, **5**, 1954–1958.
- M. P. Manoharan, A. V. Desai, G. Neely and M. A. Haque, *J. Nanomaterials*, 2008, **2008**, 49:1–49:7.
- B. Wen, J. E. Sader and J. J. Boland, *Phys. Rev. Lett.*, 2008, **101**, 175502.
- G. Feng, W. D. Nix, Y. Yoon and C. J. Lee, *Journal of Applied Physics*, 2006, **99**, 1–10.
- S. Hoffmann, F. Östlund, J. Michler, H. J. Fan, M. Zacharias, S. H. Christiansen and C. Ballif, *Nanotechnology*, 2007, **18**, 205503.
- A. Desai and M. Haque, *Sensors and Actuators A: Physical*, 2007, **134**, 169–176.
- R. Agrawal, B. Peng, E. E. Gdoutos and H. D. Espinosa, *Nano Letters*, 2008, **8**, 3668–3674.
- X. Shen, P. B. Allen, J. T. Muckerman, J. W. Davenport and J.-C. Zheng, *Nano Letters*, 2007, **7**, 2267–2271.
- R. Agrawal, J. T. Paci and H. D. Espinosa, *Nano Letters*, 2010, **10**, 3432–3438.
- M. J. Spencer, *Progress in Materials Science*, 2012, **57**, 437–486.
- S. Xu and Z. Wang, *Nano Research*, 2011, **4**, 1013–1098.
- J. Wang, A. Kulkarni, K. Sarasamak, S. Limpijumnong, F. Ke and M. Zhou, *Phys. Rev. B*, 2007, **76**, 172103.
- J. Wang, P. Xiao, M. Zhou, Z. R. Wang and F. J. Ke, *Journal of Applied Physics*, 2010, **107**, 023512–023517.
- Z.-H. Hong, T.-H. Fang and S.-F. Hwang, *Computational Materials Science*, 2011, **50**, 1944–1950.
- K. Momeni and H. Attariani, *Phys. Chem. Chem. Phys.*, 2014, **16**, 4522–4527.
- J. He, S. Nagao, J. Wu and Z. Zhang, *Proceedings of the 24th Nordic Seminar on Computational Mechanics*, 2011, 244–247.
- L. Dai, W. C. D. Cheong, C. H. Sow, C. T. Lim and V. B. C. Tan, *Langmuir*, 2010, **26**, 1165–1171.
- W. Lee, J. Chang, S. Ju, M. Weng and C. Lee, *Nanoscale Research Letters*, 2011, **6**, 352.
- D. J. Binks and R. W. Grimes, *Journal of the American Ceramic Society*, 1993, **76**, 2370–2372.
- A. J. Kulkarni, M. Zhou and F. J. Ke, *Nanotechnology*, 2005, **16**, 2749.
- G. J. Soldano, F. M. Zanotto and M. M. Mariscal, *RSC Adv.*, 2015, **5**, 43563–43570.
- D. Raymand, A. C. van Duin, M. Baudin and K. Hermansson, *Surface Science*, 2008, **602**, 1020–1031.
- D. Raymand, A. C. van Duin, D. Spångberg, W. A. G. III and K. Hermansson, *Surface Science*, 2010, **604**, 741–752.
- S. Plimpton, *Journal of Computational Physics*, 1995, **117**, 1–19.
- S. A. P. A. Y. G. H. M. Aktulga, J. C. Fogarty, *Parallel Computing*, 2012, **38**, 245–259.
- P. Giannozzi, S. Baroni, N. Bonini, M. Calandra, R. Car, C. Cavazzoni, D. Ceresoli, G. L. Chiarotti, M. Cococcioni, I. Dabo, A. Dal Corso, S. de Gironcoli, S. Fabris, G. Fratesi, R. Gebauer, U. Gerstmann, C. Gougousis, A. Kokalj, M. Lazzeri, L. Martin-Samos, N. Marzari,

- F. Mauri, R. Mazzarello, S. Paolini, A. Pasquarello, L. Paulatto, C. Sbraccia, S. Scandolo, G. Sciauzero, A. P. Seitsonen, A. Smogunov, P. Umari and R. M. Wentzcovitch, *Journal of Physics: Condensed Matter*, 2009, **21**, 395502 (19pp).
- 48 D. Vanderbilt, *Phys. Rev. B*, 1990, **41**, 7892–7895.
- 49 J. P. Perdew, K. Burke and M. Ernzerhof, *Phys. Rev. Lett.*, 1996, **77**, 3865–3868.
- 50 J. H. Monkhorst and D. J. Pack, *Phys. Rev. B*, 1976, **13**, 5188–5192.
- 51 X. Huang, P. A. Quinto-Su, S. R. Gonzalez-Avila, T. Wu and C.-D. Ohl, *Nano Letters*, 2010, **10**, 3846–3851.
- 52 X. Huang, G. Li, L. B. Kong, Y. Z. Huang and T. Wu, *Nanoscale*, 2013, **5**, 11643–11648.
- 53 C. Fonseca Guerra, J.-W. Handgraaf, E. J. Baerends and F. M. Bickelhaupt, *Journal of Computational Chemistry*, 2004, **25**, 189–210.
- 54 W. Fan, H. Xu, A. L. Rosa, T. Frauenheim and R. Q. Zhang, *Phys. Rev. B*, 2007, **76**, 073302.
- 55 S. Haffad, G. Cicero and M. Samah, *Energy Procedia*, 2011, **10**, 128–137.