

Intermittent collective dynamics of domain walls in the creep regime

Matías Pablo Grassi,¹ Alejandro B. Kolton,^{1,2} Vincent Jeudy,³
Alexandra Mougin,³ Sebastian Bustingorry,⁴ and Javier Curiale^{1,4}

¹*Instituto Balseiro, Universidad Nacional de Cuyo - CNEA,
Av. Bustillo 9500, 8400 S. C. de Bariloche, Río Negro, Argentina.*

²*CONICET, Centro Atómico Bariloche, 8400 San Carlos de Bariloche, Río Negro, Argentina.*

³*Laboratoire de Physique des Solides, CNRS, Univ. Paris-Sud, Université Paris-Saclay, 91405 Orsay, France.*

⁴*Instituto de Nanociencia y Nanotecnología, CNEA-CONICET,
Centro Atómico Bariloche, 8400 San Carlos de Bariloche, Río Negro, Argentina.*

(Dated: December 10, 2018)

We study the ultra slow domain wall motion in ferromagnetic thin films driven by a weak magnetic field. Using time resolved magneto-optical Kerr effect microscopy, we access to the statistics of the intermittent thermally activated domain wall jumps between deep metastable states. Our observations are consistent with the existence of *creep avalanches*: roughly independent clusters with broad size and ignition waiting-time distributions, each one composed by a large number of spatio-temporally correlated thermally activated elementary events. Moreover, we evidence that the large scale geometry of domain walls is better described by depinning rather than equilibrium universal exponents.

I. INTRODUCTION

Domain walls (DW) in thin ferromagnetic films have become a paradigmatic system¹⁻⁶ to learn about the universal interplay between disorder, elasticity and thermal fluctuations in driven interfaces. Such physics is relevant for a large variety of experimental systems⁷⁻⁹, and for potential applications as DW are building blocks for proposed magnetic storage devices¹⁰. The caveat is that even an arbitrarily weak disorder has a rather dramatic effect on the DW dynamics, notably the occurrence of a depinning threshold^{11,12}. Below the threshold, DW are pinned at zero temperature and they present a thermally activated glassy behavior called the creep regime at finite temperature. A better understanding of the impact of disorder in the low velocity regimes is thus fundamental for a comprehensive study of DW dynamics, and of disordered elastic interfaces in general.

Most of the experimental studies on weakly driven DW motion, including very recent ones²⁻⁶, focused on the universal features of the steady DW mean velocity vs the field H and temperature T , but not in its spatio-temporal fluctuations. Such kind of study has been mostly performed close to the depinning threshold where the fluctuations are dominated by large deterministic collective events. For example, avalanche size distribution and its universal properties has been discussed in the context of Barkhausen noise¹³, contact lines of liquids⁷, crack propagation¹⁴ and even in reaction fronts in disordered flows⁸ and active cell migration⁹. Well below the depinning threshold, the phenomenology of avalanches have remained much less clear¹⁵. Recently however, theoretical studies of ultra-slow creep motion¹⁶ have unveiled rather unexpected and non trivial spatio-temporal patterns, whose elementary events strongly differ from those encountered close to the depinning threshold. Therefore, tackling experimentally a detailed statistical study of magnetization reversal events is particularly interest-

ing.

The numerical simulations reported in Ref. 16 show that creep motion of a one dimensional interface model proceeds via a sequence of *elementary events* (EE) of fluctuating sizes. These EE are the minimal thermally activated jumps that make the DW overcome energy barriers and irreversibly advance under the applied field H . The size statistics of EE display broad distributions, with a characteristic lateral size cut-off $L_{\text{opt}} \sim H^{-3/4}$ and a characteristic area size $S_{\text{opt}} \sim L_{\text{opt}}^{5/3}$. These results confirm the existence of an optimal “thermal nucleus”, as proposed in the pioneer creep theories^{11,12}. Since energy barriers for DW motion scale as $U_{\text{opt}} \sim L_{\text{opt}}^{1/3} \sim H^{-1/4}$ (Ref. 17), Arrhenius activation of these nuclei leads to the celebrated creep-law $\ln v \sim -H^{-1/4}/T$ for the mean velocity v at which the DW move under the action of a small magnetic field H . The EE are not normally distributed in size and are not independent as traditionally assumed. On one hand, below S_{opt} , EE areas are power-law distributed as $P_{\text{EE}}(S) \approx S^{-\tau_{\text{EE}}} G(S/S_{\text{opt}})$, with τ_{EE} a characteristic exponent and $G(x)$ a rapidly decaying function for $x > 1$. On the other hand, EE tend to cluster in space and time forming larger *cluster events* (CE). These CE are similar to the so called “creep avalanches” suggested by functional renormalization group calculations in Ref. 17 and experimentally noticed in Ref. 15. Such composite objects are, unlike EE, weakly correlated and have a much broader distribution of areas, $P_{\text{CE}}(S) \sim S^{-\tau_{\text{CE}}}$ with τ_{CE} a universal exponent. These interesting predictions were not yet evidenced experimentally nor confirmed by other theoretical approaches.

In this work we test the above scenario by a statistical analysis of the ultra slow time evolution of magnetization reversal in ferromagnetic Pt/Co/Pt thin films. For different time windows of duration Δt , we determine the size (S) distribution $P_{\text{WE}}(S) \equiv P_{\text{WE}}(S; \Delta t, T, H)$ of the ob-

served consecutive *compact* magnetization reversal area that we call “window-event” (WE). This procedure permits us to relate WE with EE and CE and to show that the features displayed by $P_{\text{WE}}(S)$ are consistent with the picture summarized above of rare localized EE acting as epicenters of large CE or “creep avalanches”, each made of a large number of spatio-temporally correlated EE. Furthermore, our analysis of the intermittent collective DW motion allows to characterize the statistics of waiting times between epicenter EE, thus going beyond the “geometric” predictions of Ref 16.

II. METHODS

Experiments were mainly performed on a Pt(4.5 nm)/Co(0.7 nm)/Pt(3.5 nm) thin ferromagnetic film with perpendicular magnetic anisotropy. A polar magneto-optical Kerr effect (PMOKE) microscope was used to image magnetic domains. In order to characterize the DW dynamics, starting with a seed magnetic domain, a train of magnetic field pulses of duration t and intensity H were applied perpendicular to the film plane to favour the growth of the initial domain. The DW velocity was then computed following a standard differential protocol. After identifying the creep regime in the $H-T$ plane by fitting the creep-law $\ln v \sim -H^{-1/4}/T$, we fix T to two possible values, room temperature and 50 °C, and choose $H = 46.1$ Oe and $H = 24.2$ Oe respectively, such that $v \sim 1$ nm s⁻¹ in each case. We then analyze the magnetization reversal events at each temperature, for a total applied field time $t = 27000$ s. Since the characteristic areas of EE are expected to scale as $S_{\text{opt}} \sim H^{-5/4}$, and the energy barriers for nucleation as $U_{\text{opt}} \sim H^{-1/4}$, choosing fields deep in the creep regime allows us to maximize, in principle, our spatial and temporal sensitivity to intrinsic collective events. For these fields we indeed observe a clear intermittent (i.e. not smooth) growth. To characterize it statistically, during the long-time magnetic field pulse we stroboscopically observe the growth at intervals Δt , such that $t \gg \Delta t$. The duration Δt is much larger than the acquisition time of each image, and much smaller than the pulse time t so to collect a large number of events. This allows us to compute their area distribution, $P_{\text{WE}}(S)$, for different Δt and T . Although we mainly report results for one region of a specific sample, we have also performed less detailed but similar measurements in other regions of the same sample and also in a different material and checked robustness of our results. We discard WE touching any border of the region of interest in order to not underestimate their area and make a proper comparison with theoretical predictions. We have checked that this protocol does not affect the tails of $P_{\text{WE}}(S)$ for the time windows Δt used. We refer the reader to appendix A for further details on our experimental setup and protocols. Magnetization reversal events were previously obtained in irradiated Pt/Co/Pt samples¹⁵, identifying between 30 and 50 events depend-

ing on field values. In the present work we were able to obtain thousands of WE, thus allowing a more precise statistical description, amenable to comparison with the universal theoretical predictions.

III. RESULTS

A. Domain wall motion within the creep regime

The obtained field dependence of domain wall velocity for the analyzed sample is presented in Fig. 1(a). The figure shows the evolution of the velocity as a function of the magnetic field over eight orders of magnitude. Within the creep regime, thermal activation over a field dependent energy barrier leads to a stretched exponential increase of the velocity, given by^{1,11,12,17}

$$v = v_0 \exp \left[-\frac{T_d}{T} \left(\frac{H}{H_d} \right)^{-\mu} \right], \quad (1)$$

where v_0 is a temperature dependent velocity⁴, T the temperature, $k_B T_d$ a typical energy scale coming from the competition between elasticity and disorder (k_B being the Boltzmann constant), H_d the depinning field and $\mu = 1/4$ the universal creep exponent. As shown in Fig. 1(b), a straight line with a negative slope in a plot of $\ln v$ against $H^{-1/4}$ confirms that the measured velocities are within the creep regime, and in addition that the system belongs to the universality classes of one dimensional elastic systems displacing in a two dimensional media, with a random-bond type of disorder and short-range elasticity. The fit to the creep formula of Eq. (1) for the two temperatures we analyzed are

$$\ln[v \text{ m}^{-1}\text{s}] = -128(1)(\text{Oe})^{1/4} H^{-1/4} + 27.6(3), \quad (2)$$

$$= -100(2)(\text{Oe})^{1/4} H^{-1/4} + 24.4(5) \quad (3)$$

at $T = \text{RT}$ [Eq.(2)] and $T = 50^\circ\text{C}$ [Eq.(3)]. This data, the experimental estimates for the depinning field H_d , the depinning temperature T_d and key characteristic scales are reported in Table I.

TABLE I. Characteristic depinning values for the studied temperature and field values: H_d is the depinning field, T_d is the depinning temperature, $H_d^{1/4} \frac{T_d}{T}$ is the slope of the creep plot [see Eqs. (2) and (3)], and T/T_d and $\left(\frac{T}{T_d}\right) \left(\frac{H}{H_d}\right)^{1/4}$ are related to the distribution of waiting times as discussed in Sec. III E.

| | | |
|---|------|------|
| $T[\text{K}]$ | 293 | 323 |
| $H[\text{Oe}]$ | 46.1 | 24.2 |
| $T_d[\text{K}]$ | 7142 | 6369 |
| $H_d[\text{Oe}]$ | 760 | 650 |
| $H_d^{1/4} \frac{T_d}{T} [\text{Oe}^{1/4}]$ | 128 | 100 |
| $\frac{T}{T_d}$ | 0.04 | 0.06 |
| $\left(\frac{T}{T_d}\right) \left(\frac{H}{H_d}\right)^{1/4}$ | 0.02 | 0.02 |




FIG. 1. (a)-(b) Velocity-field characteristics for ultrathin Pt/Co/Pt magnetic thin film in different scales. In (b) the fitted solid line confirms agreement with the creep velocity law: $\ln v \sim H^{-1/4}$. The red point corresponds to a single long pulse of duration $t = 27000$ s at a small field of $H = 46.1$ Oe and room temperature (RT). The total reversed area over this long pulse is indicated in (c) and corresponds to $v = 1.710^{-9}$ m/s. During this long pulse PMOKE images were taken every $t_0 = 15$ s, allowing to identify $N_{\text{WE}}(t_0, t) = 1151$ magnetization reversal events or “window events” (WE), highlighted over the image. The color scale corresponds to the time at which each WE was observed.

With the aim of pursuing the characterization of small magnetization reversal events responsible of the creep motion of elastic systems, one should consider that the typical area size S_{opt} of the “optimal thermal nuclei” responsible for the velocity of Eq.(1) dramatically increases when the magnetic field decreases, as $S_{\text{opt}} \propto H^{-\nu_{\text{eq}}(1+\zeta_{\text{eq}})}$, with ν_{eq} and ζ_{eq} positive universal exponents^{1,11,12,17}. Since velocity follows a stretched exponential dependence with S_{opt} ^{11,12}, decreasing the magnetic field implies to perform very long time experiments. Therefore, after nucleation of a single domain, a small magnetic field ($H = 46.1$ Oe) is applied during a single long time pulse ($t = 27000$ s, i.e. 7.5 hours), reaching a velocity $v = 1.710^{-9}$ m/s. The velocity-field data thus obtained is indicated as a red point in Fig. 1(b), and the differential image shown in Fig. 1(c) corresponds to the full displacement of the domain wall under these conditions. In order to identify magnetically reversed regions (WE), during the total long pulse time t , PMOKE images were taken every $t_0 = 15$ s, which corresponds to the minimum time window Δt . During the image acquisition the magnetic field remained always ON. Consecutive images were subtracted and, since the velocity is small ($v = 1.710^{-9}$ m/s), most of differential images do

not show a clear advance of the domain wall. Eventually a magnetization reversal region resulting in a local advance of the domain wall position is observed. After the whole long time pulse experiment, the total reversed area (indicated in Fig. 1(c)) is fragmented into many small spatially compact regions obtained from the subtraction of consecutive images taken after t_0 . The number of WE, is $N_{\text{WE}}(t_0, t) = 1151$ and are highlighted with a color code over the image of the reversed area in Fig. 1(c). Due to the characteristics of the used PMOKE microscope and the image analysis, the smallest detectable displacement of the domain wall correspond to events close to $0.3 \mu\text{m}^2$ (25 pixels).

B. Event areas




FIG. 2. Sequences of magnetization reversal areas (WE) detected for different time windows of duration Δt , for $T = \text{RT}$ and $H = 46.1$ Oe. The color scale corresponds to the time at which each WE, delimited by contours lines, was detected.

In Fig. 2 we show typical WE sequences, for four different values of Δt , from a 15 s to 120 s. We can appreciate that, for a given growth, each Δt induces a particular partition of the total reversed area of the sequence. At large Δt the coalescence of several smaller WE corresponding to smaller Δt becomes evident.

In Fig. 3(a),(b) we compare size distributions $P_{\text{WE}}(S)$, from $\Delta t = 15$ to 180 s at room temperature $T = \text{RT}$ and a field $H = 46.1$ Oe, and from $\Delta t = 20$ to 160 s at $T = 50$ °C and a field $H = 24.2$ Oe, respectively. The first remarkable feature of all these distributions is their broadness, which can be roughly described by $P_{\text{WE}}(S) = S^{-\tau_{\text{WE}}} G_{\text{WE}}(S/S_{\text{WE}})$, where τ_{WE} is an effective power-law exponent and S_{WE} the cut-off value such that the function $G_{\text{WE}}(x)$ is constant for small x and decays faster than a power-law for $x \gtrsim 1$. Quantitatively similar size-distributions were observed in different regions of the same sample and also in other kind of magnetic films (see appendix A).




FIG. 3. WE area distributions for increasing window times Δt (as indicated) at RT and $H = 46.1$ Oe (a) and at $T = 50^\circ\text{C}$ and $H = 24.2$ Oe (b). In both cases $v \sim 1$ nm s $^{-1}$. At small S we compare the initial decay of $P_{\text{WE}}(S)$ with $S^{-\tau_{\text{CE}}}$, with $\tau_{\text{CE}} \approx 1.11$, where τ_{CE} corresponds to depinning avalanches. (c) The collapse scaling shows that the data of (a) and (b) displays a large size cut-off scaling $S_{\text{WE}} \sim (\Delta t/t^*)^{1/2}$, with t^* an H and T dependent characteristic time. (d) Effective power-law exponents τ_{WE} for $P_{\text{WE}}(S)$ vs $\Delta t/t^*$.

Both τ_{WE} and the large-size cut-off S_{WE} depend on Δt . As can be appreciated in Fig. 3 (a)-(b) S_{WE} increases with Δt , more specifically $S_{\text{WE}} \sim (\Delta t/t^*)^{1/2}$. The fair collapse of $P(S)\Delta t^{1/2}$ vs $S/\Delta t^{1/2}$ shown in Fig. 3(c) confirms this dependence. Here, $t^* \equiv t^*(T, H)$ is a characteristic time. Concomitantly, in Fig. 3(d) we show that $\tau_{\text{WE}} \approx 1$ for the smallest $\Delta t/t^*$ for the whole data of Figs 3(a),(b). Note also that the same t^* that describes the $S_{\text{WE}}(T, H)$ -dependence allows to build a master curve for τ_{WE} vs. $\Delta t/t^*$. For the characteristic times t^* we find $t_{50\text{C}}^* \approx 1$ s at $T = 50^\circ\text{C}$, $H = 24.2$ Oe and $t_{\text{RT}}^* \approx t_{50\text{C}}^*/3$ at $T = \text{RT}$, $H = 46.1$ Oe. Therefore $S_{\text{WE}} \approx (\Delta t)^{1/2} \mu\text{m}^2\text{s}^{-1/2}$ in the first case, and $S_{\text{WE}} \approx (3\Delta t)^{1/2} \mu\text{m}^2\text{s}^{-1/2}$ in the second one.

Since EE of Ref. 16 are power-law distributed with an exponent $\tau_{\text{EE}} \approx 1.17$ it is tempting to directly compare small Δt WE, which are also typically small, to EE. A rough estimate for the Pt/Co/Pt films we study shows that the largest EE are of the order of $S_{\text{opt}} = 10^{-3}(H_d/H)^{1.25} \mu\text{m}^2$, where H_d is the depinning field¹⁸. Since $H_d \approx 637$ Oe, and our lowest field is $H = 46$ Oe, we get that $S_{\text{opt}} \sim 10^{-5} \mu\text{m}^2$, which is clearly well below our PMOKE resolution of roughly $0.3 \mu\text{m}^2$ (25 pixels). We thus conclude that our detected WE can not

be single EE, but the sum of a large number of them. Namely, if in a time window Δt we have \mathcal{N}_{EE} such events, of sizes $s_1, s_2, \dots, s_{\mathcal{N}_{\text{EE}}}$, compactly grouped in a WE, its random area is $\mathcal{S}_{\text{WE}} \approx \sum_{i=1}^{\mathcal{N}_{\text{EE}}} s_i$. The statistics of \mathcal{S}_{WE} thus directly relates to the statistics of EE random sizes s_i contributing to the same WE and of their Δt dependent and fluctuating number \mathcal{N}_{EE} .

Given the small area of the EE compared to our detected WE, a pure statistical analysis is convenient. If the EE were considered independent and accumulating at a well defined rate on each WE, by virtue of the central limit theorem we would naively expect $P_{\text{WE}}(S)$ to develop an approximate gaussian shape around $\mathcal{N}_{\text{EE}}\bar{s}$. $P_{\text{WE}}(S)$ shows no tendency to approximate a normal nor even a peaked distribution however: it is broad, even for Δt in the minutes time scale. To interpret this it is worth recalling that the central limit theorem tell us that $\mathcal{S}_{\text{WE}} \approx \sum_{i=1}^{\mathcal{N}_{\text{EE}}} s_i$ should converge to a Gaussian distribution if \mathcal{N}_{EE} is large enough and the s_i have finite variance and short-ranged correlations¹⁹. The EE have finite variance and, although they appear to be spatially correlated, there is no evidence of correlation between their areas¹⁶. We hence interpret that \mathcal{N}_{EE} must be a strongly fluctuating quantity for all the Δt analysed. Indeed, we experimentally observe for a fixed Δt well defined bursts of magnetic activity, with $\mathcal{S}_{\text{WE}} \gg 0.3 \mu\text{m}^2$, coexisting with WE in the resolution edge $\mathcal{S}_{\text{WE}} \gtrsim 0.3 \mu\text{m}^2$, at the same H and T . Since any PMOKE resolved area $\mathcal{S}_{\text{WE}} > 0.3 \mu\text{m}^2$ has a large number of EE we arrive to the first important observation of our paper: EE are strongly clustered spatio-temporally.

C. Domain Wall roughness

The results of the previous section are consistent with the EE clustering predicted for simple domain wall models^{16,20}. To go beyond, since EE are too small to be experimentally resolved, one is immediately tempted to compare our experimentally resolved WE with the predicted CE. Indeed, unlike EE, CE are not expected¹⁶ to be strongly correlated as we also observe for WE. Moreover, the predicted value for $\tau_{\text{CE}} \approx 1.11$ is only slightly above $\tau_{\text{WE}} \approx 1$ observed in Fig. 3(d) for the smallest Δt . To argue that WE may indeed approach the single intrinsic CE in the small Δt limit, we start by noting that the same scaling of zero temperature depinning avalanches, $S_i \sim L_i^{1+\zeta_d}$, is also expected for CE¹⁶ at finite temperature. In Fig. 4(a) we analyse for $T = \text{RT}$ the approximately oblong shapes of WE by plotting the areas S_i of each WE sampled from a long sequence, versus their corresponding lateral size L_i , defined as the major axis length of the reversed blobs. A crossover is observed at $S \approx 2 \mu\text{m}^2$ below which we observe a $S_i \sim L_i^{2.25}$ scaling²¹. The two main candidate depinning universality classes that are consistent with the observed creep law $\ln v \sim H^{-1/4}/T$ are the 1d quenched-Edwards-Wilkinson (qEW), and the 1d quenched-Kardar-Parisi-

Zhang (qKPZ). The first predicts $\zeta_d \approx 1.25^{22}$ while the second $\zeta_d \approx 0.63^{23-25}$. Only the qEW value is in good quantitative agreement with Fig. 4(a), in the small size WE limit²⁶. In addition Fig. 3(d) is quantitatively consistent with the relation $\tau_{\text{CE}} = 2 - 2/(1 + \zeta_d) \approx 1.11$ predicted for qEW. To investigate this issue in Fig. 4(b) we computed the squared width $W^2(L) \equiv \overline{u_L^2(x)} - \overline{u_L(x)}^2$ from different small segments of size L extracted from typical DW configurations, where $u_L(x)$ is the DW displacement measured with respect to the untilted segment (see Appendix B details). The scaling $W^2 \sim L^{2\zeta_d}$ is consistent with the qEW *depinning roughness exponent* $\zeta_d = 1.25$ and thus with Figs. 3(d) and 4(a). We then arrive to the second important observation of our paper: WE approach single CE in the small Δt limit and we find experimental evidence that the DW roughness and CE statistical properties are better described by depinning rather than equilibrium exponents – as theoretically predicted in Refs. 17, 27, and 28. A smaller roughness exponent 0.69 ± 0.07 was observed in extended DW in the same material in the pioneering work by Lemerle *et. al.*¹, and interpreted to be the equilibrium exponent $\zeta_{\text{eq}} = 2/3$. Such interpretation implies an observation scale below L_{opt}^{27} . However, from Ref. 1 we infer $L_{\text{opt}} \approx 0.18 \mu\text{m}$, lower than their PMOKE resolution of $0.28 \mu\text{m}$. We thus conclude that a spatial crossover from the qEW value $\zeta_d \approx 1.25$ to a *non-equilibrium* exponent $\sim 0.69 \pm 0.07$ must exist. A natural candidate is the Quenched Kardar-Parisi-Zhang (qKPZ) or directed percolation depinning exponent $\zeta_d \approx 0.63$.




FIG. 4. (a) Aspect ratio scaling of $\Delta t = 15$ s WE. The solid (dashed) line shows the expected depinning scaling $S_i \sim L_i^{1+\zeta_d}$ for qEW (qKPZ) class. (b) Scaling of the square width W^2 of DW segments of size L , for two typical configurations at RT. The solid (dashed) line shows the expected qEW (qKPZ) scaling at depinning, $W^2 \sim L^{2\zeta_d}$, with $\zeta_d = 1.25(0.63)$.

D. Event lengths

In Fig. 5(a) we show the areas S_i vs the major axis length L_i of each WE. The difference with Fig. 4(a), where $\Delta t = 15$ s, is that now we plot WE for all the Δt , from 15 s to 180 s, in order to observe the effects of large

WE. We show both the cloud obtained from raw data and an averaged version by grouping areas in small logarithmically increasing bins and by taking the corresponding average value of L_i in such groups. We compare with the depinning scaling $S_i \sim L_i^{1+\zeta_d}$, expected for cluster events (CE) in the creep regime¹⁶, both for the qEW class where $\zeta_d = 1.25$ and for the qKPZ class, where $\zeta_d \approx 0.63$. At $L_i \approx L^* = 2 \mu\text{m}$ a clear crossover is observed (indicated by the vertical line). As can be appreciated in the figure, for $L_i < L^*$ a better agreement is obtained for qEW, as compared for instance with the qKPZ class.

In Fig. 5(b) we show the (non normalized) probability distribution $P_{\text{WE}}(L)$ for all the L_i observed. As for $P_{\text{WE}}(S)$, we observe a broad distribution. If WE were a part, single, or dominated by single CE we expect indeed WE to display power law distributions similar to the ones observed for depinning avalanches, $P_{\text{CE}}(S) \sim S^{-\tau_{\text{CE}}}$ and $P_{\text{CE}}(L) \sim S^{-\tau_L}$, where τ_{CE} and τ_L are related to depinning exponents. The general exponents are well known²⁹

$$\tau_{\text{CE}} = 2 - (\zeta_d + 1/\nu_d)/(1 + \zeta_d), \quad (4)$$

$$\tau_L = \tau_{\text{CE}}(1 + \zeta_d) - \zeta_d \quad (5)$$

where ζ_d is the depinning roughness exponent and ν_d the depinning correlation length exponent. For the qEW universality class, we have $\zeta_d \approx 1.25$ and, by virtue of the statistical tilt symmetry³⁰, $\nu_d = 1/(2 - \zeta_d) \approx 1.33$. On the other hand $\zeta_d \approx 0.63$ and $\nu_d \approx 1.73$ for the qKPZ class²⁵, where the statistical tilt symmetry is broken. This yields $\tau_{\text{CE}} \approx 1.11$, $\tau_L \approx 1.25$ for the qEW class, and $\tau_{\text{CE}} \approx 1.25$, $\tau_L \approx 1.42$ for the qKPZ class. The effective power law at intermediate $L \lesssim L^*$ (indicated by the vertical line) is roughly consistent with qEW. Unfortunately however, the effective power law observed in Fig. 5(b) is roughly consistent with both classes, unlike Fig. 5(a) which is more consistent with the qEW class.

The crossover at L^* , observed in Figs. 5(a), may be associated to the CE coalescence process occurring for large WE³¹. In that case, a WE area can be written as a sum of a given number \mathcal{N}_{CE} of CE areas. $S_{\text{WE}} \approx \sum_{i=1}^{\mathcal{N}_{\text{CE}}} S_i$. Since $P_{\text{CE}}(S)$ is a broad distribution, the typical WE area is dominated by the largest areas and thus relates to the typical number of CE as $S_{\text{WE}} \sim \mathcal{N}_{\text{CE}}^{1/(\tau-1)}$. The lateral size of a WE instead satisfies an inequality $L_{\text{WE}} < \sum_{i=1}^{\mathcal{N}_{\text{CE}}} L_i$, as the fluctuating CE lateral extensions \mathcal{L}_i can now overlap. Since $P_{\text{CE}}(L)$ is also a broad distribution, we can use the same extreme value argument to estimate $L_{\text{WE}} \lesssim \mathcal{N}_{\text{CE}}^{1/(\tau_L-1)}$. Combining these results we get $S_{\text{WE}} \gtrsim L_{\text{WE}}^{(\tau_L-1)/(\tau-1)} \equiv L_{\text{WE}}^{1+\zeta_d}$. This shows that WE areas should scale with their length approximately as CE in the $L_i < L^*$ regime, as observed in Fig. 5(a). Above L^* however, where large WE become a non negligible fraction of the interface, the last scaling prediction breaks down. In section III G we discuss a simple model that quantitatively accounts for the crossover observed at L^* in the S_i vs L_i plot.




FIG. 5. (a) Aspect-ratio of WEs obtained experimentally, between the area S_i and major axis length L_i of individual WE. We display the data S_i vs L_i for WE corresponding to all values of Δt , in order to enhance the crossover behaviour and access large WE. Small WE fairly scale as CE or depinning avalanches in the qEW class, $S_i \sim L_i^{1+\zeta_d}$ with $\zeta_d \approx 1.25$ and thus $S_i \sim L_i^{2.25}$ (solid line), as compared to the qKPZ class, with $\zeta_d = 0.63$, predicting $S_i \sim L_i^{1.63}$ (dashed line). The dotted-dashed line indicates a fair $S_i \sim L_i^{1.4}$ scaling, which can be rationalized using a simple model. (b) Probability distribution (non normalized) for the major axis length L_i of the events shown in (a). In (a) and (b) a vertical line indicates the approximate location of the aspect-ratio crossover, L^* .

E. Waiting times

The behaviour at large Δt , where the probability to observe single CE in a WE decreases, is directly related to the behaviour of the large-size $P_{\text{WE}}(S)$ cut-off, S_{WE} , with Δt . In such regime we can regard each WE area as the sum of a given number \mathcal{N}_{CE} of cluster areas, $S_{\text{WE}} = \sum_{i=1}^{\mathcal{N}_{\text{CE}}} S_i$. As \mathcal{N}_{CE} can only grow irreversibly with Δt , so does the large size cut-off S_{WE} . Naively one may think that S_{WE} should linearly increase with Δt because the sum of all WE areas observed in a region of a fixed lateral size L should grow as $Lv\Delta t$ in a steady-state regime. As shown in Fig. 3(c) we find instead a sub-linear increase $S_{\text{WE}} \sim (\Delta t/t^*)^{1/2}$. To make sense of this striking observation it is instructive to regard the area S_{WE} vs. Δt as a continuous-time continuous-jump random-walk, with random CE area increments S_i and waiting times δ_i for the ignition of a new CE, such that $\Delta t = \sum_{i=1}^{\mathcal{N}_{\text{CE}}} \delta_i$. If we assume that the δ_i are distributed according to $\psi(\delta) \sim t^{*\alpha} \delta^{-(1+\alpha)}$, with $0 < \alpha \leq 1$ characterizing the

broadness of $\psi(\delta)$, we get $\Delta t \sim t^* \mathcal{N}_{\text{CE}}^{1/\alpha}$ for the typical number of events \mathcal{N}_{CE} in a Δt . Since the same heuristic arguments apply for the broadly distributed CE we get $S_{\text{WE}} \sim \mathcal{N}_{\text{CE}}^{1/(\tau_{\text{CE}}-1)}$. Combining the two last results we get $S_{\text{WE}} \sim (\Delta t/t^*)^{\alpha/(\tau_{\text{CE}}-1)}$, which fairly describes our data of Fig. 3(c) if $\alpha/(\tau_{\text{CE}}-1) \approx 1/2$. Using $\tau_{\text{CE}} \approx 1.11$ we obtain $\alpha \approx 0.05$.

Broad waiting time distributions have been heuristically derived for creep motion^{32,33}, borrowing ideas from more general random energy models (see for instance Ref. 19), and also observed numerically close to the depinning threshold³⁴. The basic idea is to assume that the EE barrier distribution behaves as $P(U) \sim \exp[-U/U^*]/U^*$ for a large barrier U , with U^* a characteristic energy (with U and U^* in units of temperature). If temperature is small enough, the typical time to overcome U is given by the Arrhenius law, $\delta \sim t^* \exp[U/T]$, with t^* a characteristic time. Changing variables we obtain $\psi(\delta) \sim \alpha t^{*\alpha} \delta^{-(1+\alpha)}$, with $\alpha \sim T/U^*$. Since clustering implies that not all EE have the same U we will argue that the δ_i corresponds to the special EE that act as CE epicenters. These EE may be associated to the ones allowing to escape from dominant configurations²⁸. Two different predictions for U^* and thus for α are found in the literature. In Ref. 32, it is assumed that $U^* \equiv T_d$, with T_d From Table I we obtain $\alpha = 0.04$ for $T = 293\text{K}$ and $\alpha = 0.06$ for $T = 323\text{K}$. Both results are in excellent agreement with our data, which gives $\alpha \approx 0.05$. In Ref. 33 on the other hand, the characteristic energy is taken as the optimal nucleous barrier $U^* \equiv T_d(H_d/H)^\mu$, with $\mu = 1/4$ for the one dimensional elastic string. The exponent is thus again nonuniversal but now it is also field dependent, $\alpha \approx (T/T_d)(H/H_d)^\mu$. From table I we obtain $\alpha \approx 0.02$ both for the two temperatures and their corresponding fields. This value is only slightly below but is again of the order of $\alpha \approx 0.05$ we infer from our measurements. Both predictions are in rough agreement with the empirical $\alpha \approx 0.05$ we obtain from the time-scaling of S_{WE} we observe in Fig. 3(c) for the two temperatures. It would be interesting to perform a more systematic study as a function of T and H to further test these theories. The previous observations lead us to argue that WE give access not only to the CE area (at small Δt) but also to the waiting-time statistics (at larger Δt). As CE start at a seed EE, the δ_i must be controlled by their energy barrier distribution³⁵.

F. Event correlations

In order to further test the connection between WE and CE we have also studied correlations from the spatio-temporal correlations of the registered positions x_i of the N measured WE epicentres. To do that we used the mean square distance $\langle \delta^2 x(\mathcal{T}) \rangle \equiv \sum_{i=1}^N [x_{i+n} - x_i]^2 / N$, which depends only on the temporal separation $\mathcal{T} = nt_0$. For non-correlated WE epicentre sequences, $\langle \delta^2 x(\mathcal{T}) \rangle$ tends to a constant value $C = (L_0+1)(L_0+2)/2$, where L_0 is ap-

proximately the length of the DW in units of the spatial discretization³⁶. Figure 6 shows $\langle \delta^2 x(\mathcal{T}) \rangle / C$ measured at




FIG. 6. Normalized mean square distance $\langle \delta^2 x(\mathcal{T}) \rangle / C$ as a function of \mathcal{T} , measured at $T = RT$ and $H = 46.1$ Oe.

$T = RT$ and $H = 46.1$ Oe. One can see that even for short \mathcal{T} it becomes approximately constant as expected for uncorrelated events (note that $\langle \delta^2 x(\mathcal{T}) \rangle / C > 1$ for large \mathcal{T} due to an underestimation of the length of DW). We hence conclude that WE are very weakly correlated in sharp contrast with the predicted EE correlations in Ref. 16 and consistent to what is predicted for CE and more generally for depinning avalanches. This observation further confirms our identification of WE with single CE or with coalesced groups of them, for small or large Δt respectively.

G. Heuristic model for large WE

Summing up, our results are consistent with the predictions of Ref.16 after identifying the small Δt WE with the predicted CE. At large Δt WE can not be single CE however, and deviations from the predicted properties for CE are expected. This is already apparent in Fig. 5(a) where large WE display a clearly different length to area aspect ratio than the expected for CE. Moreover, Fig. 5(a) shows a clear crossover from the expected $S_i \sim L_i^{1+\zeta_d}$ CE behaviour to a different behaviour, rather well described by a new power-law, $S_i \sim L_i^{1.4}$. There is no theoretical predictions yet for this crossover so we propose here a simple, heuristic model.

A very simple model can explain the behaviour of S_i vs L_i observed experimentally, shown in Fig. 5(a). The idea is to think WE as the compact objects formed by random deposition of simulated CE, with a lateral sizes L_i sampled from $P_{\text{CE}}(L) \sim L^{-\tau_L}$. We can also assume, for simplicity, that the corresponding areas satisfy a deterministic relation $S_i = L_i^{1+\zeta_d}$, assumption that leads automatically to $P_{\text{CE}}(S) \sim S^{-\tau_{\text{CE}}}$, with τ_L , τ_{CE} and ζ_d




FIG. 7. A simple model for understanding the area vs major axis length of WEs. (a) Simulation results for the model (compare them experimental results in Fig. 5(a)). The solid line indicates the qEW depinning scaling, and the dashed dotted line the effective power law observed at large WE. The color bar indicates number of randomly deposited CEs. Results are reported in arbitrary units. (b) Probability distribution for percolation, as a function of the number of randomly deposited CE. (c) Average aspect-ratio scaling versus number of CE. (d) From bottom to top, four actograms showing the growth of compact WE as we increase the number of deposited CE (as indicated by the color-bar). The actograms display segments centered at uniformly distributed epicenters, whose size equals the lateral extension of the growing WE. When the system percolates, i.e. a single WE spans the system (set to unity), the actogram is reseted and a new deposition process starts.

related by Eqs.(4) and (5). Both assumptions are reasonable approximations according to creep simulations¹⁶. To simulate this model we generated such events in the interval $[0, 1]$, sequentially increasing the number of deposited CE. The process starts with one WE which equals the first deposited CE. Adding more CE may produce more WE (specially for small number of deposited CE) or can decrease their number due to the possible coalescence with an existing WE, if the new CE overlaps it. When a coalescence between a new CE and an existing WE takes place, the area of the resulting WE is the sum of the new CE area with the previous area of the WE, but the length of the new WE can either remain constant or increase at its left, right or both corners simultaneously.

In more rare cases the new CE can overlap more than one WE. The process finishes when a single WE spans the whole interval, i.e. when the deposited CE percolate the system. To make statistics over many sequences, at this point we reset the simulation and restart adding a first CE into a new actogram. Fig. 7(d) shows actograms corresponding to four runs.

To be concrete, for the simulations we use the values $\zeta_d = 1.25$, $\tau = 1.11$ and $\tau_L = \zeta_d$ corresponding to the 1d qEW depinning class. We sample the epicenter of each CE from a uniform distribution in the interval $[0, 1]$ and its lateral size l_i by $l_i = 0.05[r(l_{\max}^{\tau_L+1} - l_{\min}^{\tau_L+1}) + l_{\min}^{\tau_L+1}]^{1/(\tau_L+1)}$ with $l_{\min} = 10^{-5}$ and $l_{\max} = 1.5$, and r a different uniform random number in the interval $[0, 1]$. This produces a power-law distribution $P_{\text{CE}}(l) \sim l^{-\tau_L}$ with a cut-off at l_{\max} . The area of such CE is simply $s_i = l_i^{1+\zeta_d}$. Using different parameters yields qualitatively similar results.

We now discuss the results of the model. In Fig. 7(a) we show that the model reproduces the main features observed experimentally in Fig. 5(a). Small WE, below a characteristic crossover scale, display the $S_i \sim L_i^{2.25}$. This is natural, as most of the small WE are individual CE. At approximately $L^* \sim 0.07$ there is a crossover towards $S_i \sim L_i^{1.4}$ for large WE. Remarkably, this new exponent is indistinguishable from the one we obtain experimentally (see Fig. 5(a)). We leave for a future study to understand the origin and possible universality of this new exponent. It is worth noting however, that the crossover may be associated to the lateral acceleration that occurs when the WE almost percolate the $[0, 1]$ interval. In Fig. 7(b) we show the probability to percolate as a function of the number of deposited CE. Most of the points in Fig. 7(a) in the $S_i \sim L_i^{1.4}$ regime, belong to states with a high probability to percolate. It is also worth noting that finite size effects, due to the finiteness of the interval and the broad range of the CE lateral size distribution play an important role here. In 7(c) we show that the average anisotropic aspect-ratio $S_i/L_i^{2.25}$ is unity only for a small number of CE, but then decreases implying an accelerated lateral growth of WE, compared with the area growth. This effect may produce the crossover and the downward deviation appreciated in Fig. 7(a) and also experimentally shown in Fig. 5(a). For an even larger number of CE, the aspect-ratio increases as large WE tend to completely overlap with most of the new CE and thus increase their areas without modifying its lateral size. Those states are near to percolate but need a rare CE to overlap the voids between the few remaining WE.

The model presented has some unphysical features. In particular, the random deposition process implies, in the long time limit, a growing interface with a non-stationary width. The model describes satisfactorily the crossover in S_i vs L_i observed in the experiments however, so the necessary surface relaxation effects or correlations that may make the width to saturate are not relevant for the regime we aim to describe. In addition, the number of deposited CE does not strictly represent time. Broadly

distributed times between random depositions could be easily added however, in order to further test the picture suggested by the experiments. Particularly, to reproduce the area and lateral size distributions as a function of the window time Δt found experimentally.

IV. CONCLUSIONS

From our results the following picture emerges. Creep dynamics is driven by EE with a broad size distribution and a large size cut-off controlling the mean velocity. The seed EE that trigger a cascade of extra EE are separated by broadly distributed waiting times. Repeated, this collective process of ignition and correlated growth produce independent CE statistically very similar to depinning avalanches, that may coalesce into larger compact objects. Hence, CE can be truly regarded as “creep avalanches”. The described picture, that drastically changes the naive view of creep motion as independent thermally nucleated displacements, is likely to appear not only in other magnetic films but in the creep regime of other disordered elastic systems in general.

ACKNOWLEDGMENTS

We thank E. Ferrero, A. Rosso, E. Jagla, G. Durin, T. Giamarchi, P. Le Doussal, L. Foini, V. Lecomte, and J. L. Barrat for enlightening discussions. We thank D. Jordan for his help on digitizing DW. This work was partly supported by grants PIP11220120100250CO/CONICET, PICT2016-0069/FONCyT and UNCuyo 06/C490 and C017, from Argentina. The France-Argentina project ECOS-Sud No. A12E03 is also acknowledged.

Appendix A: Samples & Experimental Protocol

Experiments were mainly performed on a Pt/Co/Pt ultrathin ferromagnetic film, a prototypical system which has been the focus of many studies of domain wall motion^{1,2,4,5,37-40}. The studied sample was a Pt(4.5nm)/Co(0.7nm)/Pt(3.5nm) thin film, with the thickness of each layer indicated in parenthesis. The film was sputter grown at 300 K on etched Si/SiO₂ substrate. The magnetic response of this system to an external out-of-plane magnetic field is characterized by a square magnetic cycle with a well defined remnant magnetization, typical of systems with perpendicular magnetic anisotropy².

Polar magneto-optical Kerr effect (PMOKE) microscopy has been used to image magnetic domains after applying magnetic field pulses perpendicular to the film plane. After fully magnetizing the sample in one direction, a short pulse in the opposite direction and of intensity $H = 130$ Oe was first applied in order to nucleate a seed magnetic domain. Then, a second pulse of duration

t and intensity H was applied to favour the growth of the initial magnetic domain. DW velocity was then computed as the ratio between the linear advance of the DW linear advance Δx and the pulse duration, $v = \Delta x/t$. Experiments were performed at $T = \text{RT}$ (room temperature) and $T = 50^\circ\text{C}$. To measure velocities between 10^{-9} m/s and 10^{-1} m/s pulses of different amplitude and duration were used. In all the cases, the total number of pulses was 15 or more and the rise time of the pulses was more than one order of magnitude faster than the pulse duration. The shortest pulse was 1 ms and the largest one 1800 s. Due to the spatial resolution of our microscope, for velocities smaller than 10^{-8} m/s we observed that there was no difference in the observed DW velocity if the magnetic field was ON or OFF during the image acquisition. In all the cases given the illumination condition, the used shutter time of the camera was 200 ms.

Although we mainly report results for one region of a specific sample, we have made similar measurements in other regions of the same sample and also in a Pt(6nm)/[Co(0.2nm)/ Ni(0.6nm)]₃/Al(5nm) sample, where the numbers in parenthesis stand for thickness and the ferromagnetic layer consists in a stack of three Co(0.2nm)/ Ni(0.6nm) bilayers (for more information about these samples and their domain wall dynamics see Refs. 41 and 42). In both cases the results are consistent with the main universal results reported for the specific region of the Pt/Co/Pt sample in Section III.




FIG. 8. Histograms for the $N_{\text{tot}}(t_0, t) = 1151$ WE shown in Fig. 1(c), obtained by comparing consecutive images taken every $\Delta t = t_0 = 15$ s at $T = \text{RT}$ and $H = 46.1$ Oe. The histogram with uniform binning is presented in the left panel, while in the right panel a logarithmic binning is used for same WE. Power-law behaviour at small sizes can be described with $P_{\text{WE}}(S) \sim S^{-\tau_{\text{WE}}}$ with the distribution exponent $\tau_{\text{WE}} \approx 0.76 \pm 0.1$.

Magnetization reversal events were previously obtained in irradiated Pt/Co/Pt samples¹⁵, identifying between 30 and 50 events depending on field values. In the present work, as we previously anticipated, we were able to obtain a large amount of WE. This represents a quantitative progress in view of the fact that this allows us to perform a deeper statistical description of the data. Figure 8 shows the obtained histogram of the 1151 WE

areas shown in Fig. 1(c) by comparing consecutive images taken every $t_0 = 15$ s. Since we are seeking power-law like distributions and their effective exponents, it is convenient to use logarithmic binning. In the right panel of Fig. 8 we use the same WE used in the left panel to build a new histogram. In this case, dividing the number of events per interval by the width of the interval, the probability distribution is obtained. Fig. 8 shows a power-law signature at small size values with a cut-off around $3 \mu\text{m}^2$. The distribution is of the form $P_{\text{WE}}(S) = S^{-\tau_{\text{WE}}}G_{\text{WE}}(S/S_{\text{WE}})$, where τ_{WE} is the power-law exponent and S_{WE} the cut-off value such that the function $G_{\text{WE}}(x)$ rapidly decays for $x \gtrsim 1$.

For a proper comparison with theoretical predictions we discarded in the statistical analysis events touching the borders of the region of interest, i.e. the observation region, otherwise their area would be underestimated. This may affect however the tails of the size distribution, corresponding to large events, with a lateral size of the order or larger than the lateral size L of the observation region. For the range of time windows Δt we consider WE of lateral size L are extremely rare however. Indeed we observe a Δt -dependent but clearly L -independent cut-off in our distributions, growing as $\Delta t^{1/2}$ (with a temperature dependent prefactor). Such Δt dependence is used to estimate the waiting time distribution exponent for cluster “ignition events”. On the other hand, the power-law decay effective exponent of WE, which is also central to our analysis and for the comparison with theory is not sensible to the tails. This justifies our event detection protocol.

To evidence the robustness of our results, in Fig. 9 we show results for the event area distribution measurements done in a different region of the same Pt(4.5nm)/Co(0.7nm)/Pt(3.5nm) sample (upper panel), and for a Pt(6nm)/[Co(0.2nm)/ Ni(0.6nm)]₃/Al(5nm) sample (lower panel). As can be appreciated, not only the effective power-law decay exponent is similar, but also the time dependence is qualitatively similar to the one of Fig. 3 reported in in Sec.III for the sample and region we have chosen for most of our analysis.

Appendix B: Domain wall roughness

In order to have a more direct estimate of the roughness exponent of our DW, and check consistency with our interpretation of the WE statistics, we have computed the single-value displacement field $u_L(x)$ of segments of given sizes L partitioning a larger DW configuration. Here we discuss our practical method. The displacements $u_L(x)$ for each segment are measured with respect to the straight line fitting each segment. This straight line is also used as the x -axis to parametrize the displacement field. Such an approach is justified by taking into account that the theoretical description of a directed driven interface assumes that the interface is flat in average in the direction perpendicular to the motion. The field on mag-




FIG. 9. WE area histograms obtained from a different region (upper panel) of the same Pt(4.5nm)/Co(0.7nm)/Pt(3.5nm) sample used to report most our results in the main text, and obtained for a different Pt(6nm)/[Co(0.2nm)/Ni(0.6nm)]₃/Al(5nm) sample (lower panel).

netic DW on the other hand act as a pressure, always normal to the DW. Having $u_L(x)$ for segments of different length L , we can now compute their global squared width $W^2(L) \equiv \overline{u_L^2(x)} - \overline{u_L(x)}^2$. If the interface is self-affine, we expect $W^2 \sim L^{2\zeta}$ with a well defined roughness exponent ζ . We have tested this methodology numerically on large discretized interfaces of size L_0 , with displacement field $U(x)$, where $x = 0, 1, \dots, L_0 - 1$, with different precise values of ζ . We do so by superimposing Fourier modes $U(x) = \sum_q U_q e^{iqx}$ with $q = 2\pi n/L_0$ ($n = 0, \dots, L_0 - 1$),

U_q complex hermitian gaussian amplitudes of zero mean, $\langle U_q \rangle = 0$, and variance $\langle |U_q|^2 \rangle \sim 1/q^{1+2\zeta}$ (also known as “self-affine gaussian signals”⁴³). This construction assures that the signal $U(x)$ is periodic, $U(x) = U(x + L_0)$, and self-affine with identical spectral and global exponent ζ . Finally, we compute $W^2(L)$ for these interfaces, by the partition procedure previously described. In Fig. 10 we compare $W^2(L)$ vs L with the corresponding scalings for each ζ , averaged over 10 uncorrelated numerically sampled configurations $U(x)$. A good agreement is always obtained if the fit does not include values of L larger than a fixed fraction of the order of the total size L_0 , so to have a large number of segments and to reduce boundary effects. It is worth noting that our method also allows to accurately measure values $\zeta > 1$, corresponding to super-rough interfaces. This is an advantage over the displacement correlator function




FIG. 10. Numerical test for the practical implementation used to compute W^2 for a DW. We compute W^2 for numerically generated self-affine gaussian signals of size $L_0 = 1024$ for several precise values of ζ . We average over 10 samples for each ζ . The solid lines show agreement with the expected $W^2 \sim L^{2\zeta}$. The method allows to measure super-rough cases $\zeta > 1$.

$B(x) \equiv \int_0^{L_0-x} dx_0 \overline{[u(x+x_0) - u(x_0)]^2} / (L_0 - x)$ which gives the correct global ζ , $B(x) \sim x^{2\zeta}$, only if $\zeta < 1$, otherwise it saturates to $\zeta = 1$.

¹ S. Lemerle, J. Ferré, C. Chappert, V. Mathet, T. Giamarchi, and P. Le Doussal, Phys. Rev. Lett. **80**, 849 (1998).

² P. J. Metaxas, J. P. Jamet, A. Mougin, M. Cormier, J. Ferré, V. Baltz, B. Rodmacq, B. Dieny, and R. L. Stamps, Phys. Rev. Lett. **99**, 217208 (2007).

³ K.-J. Kim, J.-C. Lee, S.-M. Ahn, K.-S. Lee, C.-W. Lee, Y. J. Cho, S. Seo, K.-H. Shin, S.-B. Choe, and H.-W. Lee, Nature **458**, 740 (2009).

⁴ J. Gorchon, S. Bustingorry, J. Ferré, V. Jeudy, A. B. Kolton, and T. Giamarchi, Phys. Rev. Lett. **113**, 027205 (2014).

⁵ V. Jeudy, A. Mougin, S. Bustingorry, W. Saverio Torres, J. Gorchon, A. B. Kolton, A. Lemaitre, and J.-P. Jamet, Phys. Rev. Lett. **117**, 057201 (2016).

⁶ R. Diaz Pardo, W. Saverio Torres, A. B. Kolton, S. Bustingorry, and V. Jeudy, Phys. Rev. B **95**, 184434 (2017).

⁷ P. Le Doussal, K. J. Wiese, S. Moulinet, and E. Rolley, Europhys. Lett. **87**, 56001 (2009).

⁸ S. Atis, A. K. Dubey, D. Salin, L. Talon, P. Le Doussal, and K. J. Wiese, Phys. Rev. Lett. **114**, 234502 (2015).

⁹ O. Chepizhko, C. Giampietro, U. Mastrapasqua, M. Nourazar, M. Ascagni, M. Sugni, E. Fascio, L. Leggio, C. Malinverno, G. Scita, S. Santucci, M. J. Alava, S. Zapperi, and C. A. M. La Porta, Proc. Nat. Acad. Sci. **113**,

- 11408 (2016).
- ¹⁰ S. S. P. Parkin, M. Hayashi, and L. Thomas, *Science* **320**, 190 (2008).
- ¹¹ T. Nattermann, *Phys. Rev. Lett.* **64**, 2454 (1990).
- ¹² L. B. Ioffe and V. M. Vinokur, *J. Phys. C* **20**, 6149 (1987).
- ¹³ G. Durin, F. Bohn, M. A. Corrêa, R. L. Sommer, P. Le Doussal, and K. J. Wiese, *Phys. Rev. Lett.* **117**, 087201 (2016).
- ¹⁴ L. Laurson, X. Illa, S. Santucci, K. Tore Tallakstad, K. J. Måløy, and M. J. Alava, *Nat. Commun.* **4**, 2927 (2013).
- ¹⁵ V. Repain, M. Bauer, J.-P. Jamet, J. Ferré, C. Chappert, and H. Bernas, *Europhys. Lett.* **68**, 460 (2004).
- ¹⁶ E. E. Ferrero, L. Foini, T. Giamarchi, A. B. Kolton, and A. Rosso, *Phys. Rev. Lett.* **118**, 147208 (2017).
- ¹⁷ P. Chauve, T. Giamarchi, and P. Le Doussal, *Phys. Rev. B* **62**, 6241 (2000).
- ¹⁸ See Supp. Mat. in Ref.16.
- ¹⁹ J.-P. Bouchaud and A. Georges, *Physics Reports* **195**, 127 (1990).
- ²⁰ V. H. Purrello, J. L. Iguain, A. B. Kolton, and E. A. Jagla, *Phys. Rev. E* **96**, 022112 (2017).
- ²¹ We show both the original noisy S_i vs. L_i curve and a smoothed curve, obtained by grouping similar areas in small bins and by assigning the average of L_i to each area bin. Indistinguishable results are obtained by binning L_i rather than S_i .
- ²² E. E. Ferrero, S. Bustingorry, and A. B. Kolton, *Phys. Rev. E* **87**, 032122 (2013).
- ²³ A. Rosso and W. Krauth, *Phys. Rev. Lett.* **87**, 187002 (2001).
- ²⁴ L.-H. Tang, M. Kardar, and D. Dhar, *Phys. Rev. Lett.* **74**, 920 (1995).
- ²⁵ A.-L. Barabási and H. E. Stanley, *Fractal Concepts in Surface Growth*, Cambridge University Press ed. (Cambridge, 1995).
- ²⁶ The downward deviation crossover for large WEs or lateral acceleration is due to coalescence effects in the proximity of a percolation transition. See Sec.III G for further details.
- ²⁷ A. B. Kolton, A. Rosso, T. Giamarchi, and W. Krauth, *Phys. Rev. Lett.* **97**, 057001 (2006).
- ²⁸ A. B. Kolton, A. Rosso, T. Giamarchi, and W. Krauth, *Phys. Rev. B* **79**, 184207 (2009).
- ²⁹ S. Zapperi, P. Cizeau, G. Durin, and H. E. Stanley, *Phys. Rev. B* **58**, 6353 (1998).
- ³⁰ M. Kardar, *Phys. Rep.* **301**, 85 (1998).
- ³¹ In our protocol, the maximum WE lateral size L_i was limited by the lateral size L_{roi} of the region of interest. We did not consider WE touching nor spanning completely the region of interest. If spanning WE were considered we would have $S_{WE} \approx v\Delta t L_{roi}$ in the long-time limit, with v the average velocity, shown in Figs. 1(a),(b).
- ³² V. M. Vinokur, M. C. Marchetti, and L.-W. Chen, *Phys. Rev. Lett.* **77**, 1845 (1996).
- ³³ C. Monthus and T. Garel, *Phys. Rev. E* **78**, 041133 (2008).
- ³⁴ E. A. Jagla, unpublished.
- ³⁵ Barrier distributions for dominant metastable states have been computed in Ref. 28 for forces below and near f_c . For small systems a roughly exponential right tail followed by a cut-off can be appreciated.
- ³⁶ L. Foini, A. Rosso, private communication.
- ³⁷ S. Emori and G. S. D. Beach, *J. Phys. Condens. Matter* **24**, 024214 (2012).
- ³⁸ K.-W. Moon, D.-H. Kim, S.-C. Yoo, C.-G. Cho, S. Hwang, B. Kahng, B.-C. Min, K.-H. Shin, and S.-B. Choe, *Phys. Rev. Lett.* **110**, 107203 (2013).
- ³⁹ A. Hrabec, N. A. Porter, A. Wells, M. J. Benitez, G. Burnell, S. McVitie, D. McGrouther, T. A. Moore, and C. H. Marrows, *Phys. Rev. B* **90**, 020402 (2014).
- ⁴⁰ A. W. J. Wells, P. M. Shepley, C. H. Marrows, and T. A. Moore, *Phys. Rev. B* **95**, 054428 (2017).
- ⁴¹ J.-C. Rojas-Sánchez, P. Laczkowski, J. Sampaio, S. Collin, K. Bouzehouane, N. Reyren, H. Jaffrès, A. Mougin, and J.-M. Georges, *App. Phys. Lett.* **108**, 082406 (2016).
- ⁴² N. B. Caballero, I. Fernández Aguirre, L. J. Albornoz, A. B. Kolton, J. C. Rojas-Sánchez, S. Collin, J. M. George, R. Diaz Pardo, V. Jeudy, S. Bustingorry, and J. Curiale, *Phys. Rev. B* **96**, 224422 (2017).
- ⁴³ A. Rosso, R. Santachiara, and W. Krauth, *Journal of Statistical Mechanics: Theory and Experiment* **2005**, L08001 (2005).